



Aalborg Universitet

AALBORG UNIVERSITY
DENMARK

Dynamic behavior of the 3CaO-1Al₂O₃ liquid

Pan, R.K.; Qiao, A.; Tao, H.Z.; Ruan, J.; Zhao, X.J.; Greaves, G.N.; Yue, Yuanzheng

Published in:
The 24th International Congress on Glass - Abstracts

Creative Commons License
Unspecified

Publication date:
2016

Document Version
Publisher's PDF, also known as Version of record

[Link to publication from Aalborg University](#)

Citation for published version (APA):
Pan, R. K., Qiao, A., Tao, H. Z., Ruan, J., Zhao, X. J., Greaves, G. N., & Yue, Y. (2016). Dynamic behavior of the 3CaO-1Al₂O₃ liquid. In *The 24th International Congress on Glass - Abstracts* (pp. 152). International Commission on Glass (ICG).

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal -

Take down policy

If you believe that this document breaches copyright please contact us at vbn@aub.aau.dk providing details, and we will remove access to the work immediately and investigate your claim.

Dynamic behavior of the 3CaO-1Al₂O₃ liquid

R.K. Pan^{1,2}, A. Qiao¹, H.Z. Tao¹, J. Ruan¹, X.J. Zhao¹, G.N. Greaves^{1,3}, Y.Z. Yue^{1,4}

¹State Key Laboratory of Silicate Materials for Architectures, Wuhan University of Technology, Wuhan 430070, China

²School of Materials Science and Engineering, Hubei University, Wuhan 430062, China

³Centre for Advanced Functional Materials and Devices, Institute of Mathematics and Physics, Aberystwyth University, Aberystwyth SY23 3BZ, United Kingdom

⁴Department of Chemistry and Bioscience, Aalborg University, DK-9220 Aalborg, Denmark

panruikun5@sina.com

Calcium aluminates (CaO)_x(Al₂O₃)_{1-x} are main components in the Earth's mantle and also in the aluminate cement, which have been studied by many researchers.^{1,2} Calcium aluminates are very fragile glass formers and do not contain typical network-forming cations. The structure of (CaO)_x(Al₂O₃)_{1-x} with $x=0.33, 0.5$ and 0.75 was investigated in a laser heated aerodynamic levitation (ADL) furnace.^{3,4} The ADL technique enables vitrifying calcium aluminates in the composition range of $0.37 < x < 0.75$, whereas the conventional melt-quenching method can vitrify only those in a much narrower x range ($0.6 < x < 0.7$).³ Kargl et al studied the viscous behavior of the CaAl₂O₄ liquid in the temperature range of 2000 to 2800 K by using ADL.⁵ Hennet et al studied the structural evolution of the fragile glass-forming liquid-CaAl₂O₄.⁶




Figure 1: Viscosity η vs T_g -scaled temperature of C3A fitted to the MYEGA equation. Viscosities near T_g were determined from the relation $\log \eta = 11.35 + \log(1/q_c(T_f))$.⁷ The slope of linear fitting to $\log(1/q_c(T_f)) \sim T_g/T_f$ plots of DSC results is the fragility m .

The 3CaO-1Al₂O₃ (C3A) bulk glass was prepared using the ADL technique. The viscosities at high temperatures (1773~2923 K) of the C3A liquid were measured using the ADL technique as shown in Figure 1. By conducting differential scanning calorimetric (DSC) measurements, we determined the glass transition temperature ($T_g=1092$ K) and the dependence of fictive temperature (T_f) on cooling rate (q_c). The temperature dependence of viscosity was fitted to the Mauro-Yue-Ellison-Gupta-Allan (MYEGA) equation.⁸ The fragility parameter m' of the C3A liquid was determined to be about 74 by extrapolating the MYEGA fitting curve to the T_g , while m was determined using DSC to be about 33. This implies that the fragile-to-strong liquid transition occurs in the C3A liquid upon cooling.⁹

- 1) G. Urbain, viscosity of liquids system CaO-Al₂O₃, Rev. Int. Hautes Temp. Ref. Fr. 20 (1983) 135-139.
- 2) J.W.E. Drewitt, L. Hennet, A. Zeidler, S. Jahn, P.S. Salmon, D.R. Neuville, H.E. Fischer, Structural transformations on vitrification in the fragile glass-forming system CaAl₂O₄, Phys. Rev. Lett. 109 (2012) 235501.
- 3) J.W.E. Drewitt, S. Jahn, V. Cristiglio, A. Bytchkov, M. Leydier, S.Brassamin, H.E Fischer, L. Hennet, Corrigendum: The structure of liquid calcium aluminates as investigated by neutron and high-energy x-ray diffraction in combination with molecular dynamics simulation methods, J. Phys.: Condens. Matter. 24 (2012) 099501.
- 4) D. Langstaff, M. Gunn, G.N. Greaves, A. Marsing, F. Kargl, Aerodynamic levitator furnace for measuring thermophysical properties of refractory liquids, Rev. Sci. Instrum. 84 (2013) 124901.
- 5) F. Kargl, C.C. Yuan, G.N. Greaves, Aerodynamic Levitation: Thermophysical property measurements of liquid oxides, Int. J. Microgravity Sci. Appl. 32 (2015) 320200.
- 6) L. Hennet, I. Pozdnyakova, A. Bytchkov, D.L. Price, Development of structural order during supercooling of a fragile oxide melt, J. Chem. Phys., 126 (2007) 074906.
- 7) Y.Z. Yue, R. von der Ohe, S.L. Jensen, Fictive temperature, cooling rate, and viscosity of glasses, J. Chem. Phys., 120 (2004)8053.
- 8) J.C. Mauro, Y.Z. Yue, A.J. Ellison, P.K. Gupta, D.C. Allan, Viscosity of glass-forming liquids, Proc. Natl. Acad. Sci. U.S.A. 106 (2009) 19780-19784.
- 9) C.Z. Zhang, L.N. Hu, Y.Z. Yue, J.C. Mauro, Fragile-to-strong transition in metallic glass-forming liquids, J. Chem. Phys. 133 (2010) 014508.